

## TEST LINER Technicle Data Sheet

Grammage( $\text{g/m}^2$ )	Moistrure(%)	Bursting Strength( $\text{Kg/cm}^2$ )	RCT(kn/m)	Cobb 60 ( $\text{g/m}^2$ )
120	6.5-8.0	3.0-3.1	1	35-40
140	6.5-8.0	3.4-3.6	1	35-40
150	6.5-8.0	3.7-3.9	2	35-40
180	6.5-8.0	4.3-4.5	2	35-40
200	6.5-8.0	4.8-5.0	2	35-40