

Fluting Medium Technique Data Sheet

BF	GSM G/M2	Cobb (45 Second)	RCT (Kg/m)		Moisture %
			MD	CD	
16	150	40-50	1.00	0.85	6%-8%
	180	40-50	1.30	1.10	6%-8%
	200	40-50	1.60	1.45	6%-8%
	250	40-50	1.90	1.70	6%-8%
	300	40-50	3.00	2.50	6%-8%
18	140	40-50	1.00	0.85	6%-8%
	150	40-50	1.15	1.10	6%-8%
	180	40-50	1.45	1.30	6%-8%
	200	40-50	1.75	1.60	6%-8%
	250	40-50	2.05	1.95	6%-8%
	300	40-50	2.80	2.55	6%-8%
<u>20</u>	140	40-50	1.15	1.10	6%-8%
	150	40-50	1.25	1.20	6%-8%
	180	40-50	1.60	1.40	6%-8%
	200	40-50	1.90	1.75	6%-8%
	250	40-50	2.20	2.10	6%-8%
	300	40-50	3.20	2.70	6%-8%